

PC/ABS Delite 635

Characteristics	Unit	Delite 635
Density 密度	g/cm ³	1.14
Tensile Strength 抗张强度	MPa	55
Elongation at break 断裂伸长率	%	130
Flexural Strength 弯曲强度	MPa	700
Izod Impact, 冲击强度 23°C	kJ/m ²	60
HDT 热变形温度 1.8MPa	°C	100
Vicat Point 维卡软化点	°C	110
Melt Index 熔融指数	g/10min	20
Mold Shrinkage 成型收缩率	%	0.5 ~ 0.7
Flammability 阻燃性	UL 94	HB